

**(19) AUSTRALIAN PATENT OFFICE**

(54) Title  
**NON-AQUEOUS ELECTROLYTIC SECONDARY BATTERY**

(51)<sup>6</sup> International Patent Classification(s)  
**H01M 004/02 H01M 004/62**  
**H01M 004/60 H01M 010/40**

(21) Application No: **2002366928** (22) Application Date: **2002.12.20**

(87) WIPO No: **WO03/054986**

(30) Priority Data

(31) Number	(32) Date	(33) Country
<b>2002-178142</b>	<b>2002.06.19</b>	<b>JP</b>
<b>2001-389259</b>	<b>2001.12.21</b>	<b>JP</b>
		<b>7</b>

(43) Publication Date : **2003.07.09**

(43) Publication Journal Date : **2003.10.02**

(71) Applicant(s)  
**SANYO ELECTRIC CO.,LTD.**

(72) Inventor(s)  
**TARUI, Hisaki; FUJITANI, Shin; MIYAKE, Masahide; FUJIMOTO, Masahisa; KOGA, Hideyuki**

[Original document](#)

# NON-AQUEOUS ELECTROLYTIC SECONDARY BATTERY

Publication number: AU2002366928

Publication date: 2003-07-09

Inventor: TARUI HISAKI; FUJITANI SHIN; MIYAKE  
MASAHIDE; FUJIMOTO MASAHISA; KOGA  
HIDEYUKI

Applicant: SANYO ELECTRIC CO

Classification:

- international: *H01M4/02; H01M4/38; H01M4/60; H01M4/62;  
H01M10/36; H01M10/40; H01M4/02; H01M4/36;  
H01M4/38; H01M4/62; H01M10/36; (IPC1-7):  
H01M4/02; H01M4/60; H01M4/62; H01M10/40*

- European:

Application number: AU2002366928 20021220

Priority number(s): JP20020178142 20020619; JP20010389259 20011221;  
WO2002JP13405 20021220


Also published as:

WO03054986 (A1)  
US2005019655 (A1)  
CN1610980 (A)  
CN100370641C (C)[View INPADOC patent family](#)[View list of citing documents](#)[Report a data error here](#)

Abstract not available for AU2002366928

Abstract of corresponding document: **WO03054986**

A non-aqueous electrolytic secondary battery provided with a positive electrode, a negative electrode and a non-aqueous electrolyte, wherein the positive electrode contains sulfur, and the non-aqueous electrolyte contains room-temperature-molten salt having a melting point of up to 60 DEG C.

Data supplied from the *esp@cenet* database - Worldwide